


3.2 Cellulose Acetate Membranes

Type 11104, 0.8 µm



Description

Cellulose acetate membranes combine high flow rates and thermal stability with very low adsorption characteristics. The 0.8 µm membrane is used for the particle filtration in samples where a low adsorption is required. The membrane is excellently suited for use in pressure filtration devices.

Color

White

Material

Cellulose acetate

Reaction to Water

Hydrophilic

Pore Size (Nominal)

0.8 µm

Structure

Symmetric

Applications and Features

Typical Applications

Particle reduction of liquid samples where no non-specific adsorption can be tolerated. Prefiltration of water with a high particle load, of media and similar samples.

Special Features

- Very low non-specific adsorption
- Excellent thermal resistance

Technical Advantages

- Minimum loss of proteins, preservatives etc.
- Autoclavable at 121°C or 134°C
- Dry heat sterilization possible
- Reliable sterile filtration

Typical Performance

Adsorption, Non-specific

Bovine serum albumin
< 10 µg/cm²

Bubble Point with Water (DIN 58355)

1.0 bar | ~ 14 psi

Burst Pressure

0.3 bar | ~ 4.4 psi

Chemical Compatibility

Compatible with aqueous solutions (pH 4–8), oils, alcohols and several other organic solvents

Extractables with Water

< 1%

Flow Rate for Air [L/m²/s 200 Pa] according to*

5.3

corresponding water flow rate: approx.
200 ml/min at Δp = 1 bar | ~14.5 psi

Sterilization Methods

Autoclaving at 121°C or 134°C, dry-heat sterilization at 160°C, ETO sterilization, γ-irradiation (25 kGy)

Thermal Resistance

180°C max.

Thickness (DIN 53105)

Approx. 120 µm

Order Numbers

13 mm diameter:

11104-013N, pack of 100

25 mm diameter:

11104-025N, pack of 100

47 mm diameter:

11104-047N, pack of 100

50 mm diameter:

11104-050N, pack of 100

142 mm diameter:

11104-142G, pack of 25

11104-142N, pack of 100

293 mm diameter:

11104-293G, pack of 25

11104-293N, pack of 100

* ASTM D737
DIN 53'887
ISO 9'237